



## *technical data sheet*

# **PATCHFIX FINE FILLER**

## ***Pre blended fine graded mineral filler***

**PRODUCT**

Patchfix Fine Filler is a Fine graded inorganic pre blended mineral filler.

**DESCRIPTION**

Patchfix Fine Filler is an inorganic pre blended mineral filler consisting of fine graded quartz aggregate for mixing with Patchfix Epoxy Binder, Techflow Epoxy Grout Techflow Epoxy Grout, Ultralevel range of levelling compounds or other Epoxy Resin binders.

**RECOMMENDED USES**

- Use for mixing with Patchfix Epoxy Binder, Techflow Epoxy Grout or other Epoxy Resin binders to produce mortars of various consistencies.
- Large sections can be repaired if used as a trowel applied mortar.
- Can produce consistencies ranging from pourable grout to high build trowellable mortars.
- Economical repairs requiring high strength.
- Non skid surfaces.
- Preparation of concrete mortars and mixers.
- Can be added to cementitious repair mortars to bulk out.
- Can be added to Ultralevel range to bulk out for thick sections.

**FEATURES AND BENEFITS**

- Compatible with most Epoxy systems.
- Compatible with most cement based systems.
- Convenient bag size.
- Economical.
- Uniform particle size grading.
- High graded quartz.

**COVERAGE / YIELD**

1 litre of mixed material will cover 1m<sup>2</sup> at 1mm thick. Refer to Tables 1 and 2.

**PACKAGING**

Patchfix Fine Filler is supplied in a 20kg polylined bag.

**PERFORMANCE PROPERTIES**

The following may be used as a guide for the quantity of Patchfix Fine Filler required to obtain a specific consistency when **Techflow Epoxy Grout** is used as a binder.

Litres of <b>Techflow Epoxy Grout</b>	Approx. weight of <b>Patchfix Fine Filler</b>	Approx. Yield (litres) (Resin and Fillers)	Mixed Consistency	Pot Life 20°C (minutes approx.)	Compressive strength at 7 Days MPa approx.	Tensile strength at 7 days MPa Approx	Flexural strength a 7 days MPa approx
1	1.7	2	Fluid Grout	40-45	110	17	32
1	5.0	4	Pourable Grout	40-50	100	15	29
1	6.0	4.5	Stiff Paste	55-65	95	14	28
1	8.0	5.7	Trowellable Mortar	60-70	90	12	26
1	9.0	6.3	Dry Mortar Trowellable	65-80	85	11	26

The following may be used as a guide for the quantity of Patchfix Fine Filler required to obtain a specific consistency when **Patchfix Epoxy Binder** is used as a binder.

Litres of <b>Patchfix Epoxy Binder</b>	Approx. weight of <b>Patchfix Fine Filler</b>	Approx. Yield (litres) (Resin and Fillers)	Mixed Consistency	Pot Life 20°C (minutes approx.)	Compressive strength at 7 Days MPa approx.	Tensile strength at 7 days MPa Approx	Flexural strength a 7 days MPa approx
1	1.7	2	Very Fluid Grout	35-45	80	16	28
1	3.4	3	Fluid Grout	40-50	75	14	26
1	5.1	4	Pourable Grout	55-65	70	13	26
1	6.8	5	Stiff Paste	55-65	90	11	25
1	8.5	6	Trowellable Mortar	55-64	70	11	24
1	10.2	7	Dry Mortar Trowellable	65-70	60	10	21

### Note:

1. For maximum adhesion of heavily filled mortars, the surface or substrate to be treated should be primed with Patchfix Epoxy Binder or Techflow Epoxy Grout unfilled before applying the mortar mix, Surface should be allowed to reach a tacky consistency before applying mortar.
2. The use of higher quantities of Patchfix Fine Filler than those shown in the application mixing table guide will result in a porous mix, which may be susceptible to ingress of aggressive chemicals,
3. Patchfix Fine Filler must be dry and moisture free.  
The presence of water in the mix will lead to lower strengths and high risk of air pockets formed by water trying to escape from the mix.

## APPLICATION INSTRUCTIONS

### SUBSTRATE AND SURFACE PREPARATION

The surfaces to which filled Patchfix Epoxy Binder and Techflow Epoxy Grout are applied must be clean, sound and free from dust and any loose particles. Cement laitance, oil, grease, mould release oil or curing compounds must be removed from concrete surfaces by using wire brush, bush hammer, scabber, grit blasting or other means. Ensure that steel rebars are also clean from grease, oil or rust. When repairing spalled or deteriorated concrete, ensure that the concrete has been cut back to sound material. Steel surfaces should be degreased with a suitable solvents such as Bostik Solvent 9907 or treated by gritblasting. In many cases where corrosion is present, wire brushing to a clean bright surface is sufficient. During application, the temperature of the substrate should not be below 5°C. Avoid high surface temperatures, shade before and during the application.

### MIXING

Follow the mixing directions as shown on Patchfix Epoxy Binder and Techflow Epoxy Grout data sheet and labels. Add the required quantity of filler as indicated in the table, Patchfix Epoxy Binder and Techflow Epoxy Grout must be mixed with a mechanical forced action mixer with a high shear stirrer.

### APPLICATION

Apply the mixed Epoxy mortar to the concrete substrate which should be primed with Patchfix Epoxy Binder and Techflow Epoxy Grout unfilled. Both Patchfix Epoxy Binder and Techflow Epoxy Grout either filled or unfilled may be applied to a damp substrate **NOT WET.**

## PRECAUTIONS

- Under no circumstances should the ratio of resin to curing agent be altered from the recommended proportions in an attempt to vary the working time. If accurate proportioning is not achieved substantial reduction in physical properties will result and complete cure will be effected.
- To obtain a trowellable high build consistency for vertical or overhead application it is recommended Patchfix Epoxy Binder be used with approximately 6-8kg of Patchfix Fine Filler per litre of Patchfix Epoxy Binder.
- DO NOT USE PATCHFIX COARSE FILLER to produce a high build mortar for a vertical application, this will result in a slump, high sag mortar which will not remain on a vertical wall.
- For the deep section grouting it is recommended that Patchfix Fine Filler is used with Techflow Epoxy Grout at 4kg of Patchfix Fine Filler per 1 litre of Techflow Epoxy Grout, depth of up to 200mm can be achieved in a single application.

## HEALTH AND SAFETY

Patchfix Epoxy Binder and Techflow Epoxy Grout contain epoxy resins and hardeners. Some people are sensitive to resins, hardeners and solvents.

- Avoid contact with skin and eyes and avoid breathing vapour.
- Use only in well ventilated areas.
- Wear suitable protective clothing, gloves and eye protection when mixing or using.
- If poisoning occurs, contact a doctor or Poisons Information Centre.
- If swallowed, DO NOT induce vomiting, give a glass of water.
- If in eyes, hold eyes open, flush with water for at least 15 minutes and see a doctor.
- If skin contact occurs, remove contaminated clothing and wash skin thoroughly with soap and water.
- Bostik Material Safety Data Sheets (MSDS are available on request to the nearest Bostik office.  
Read the MSDS and Technical Data Sheet carefully before using any product.

## CLEAN UP

Patchfix Fine Filler and Epoxy should be removed from tools and equipment as with Bostik Solvent 9907, immediately after use.

## STORAGE

Patchfix Fine Filler has an indefinite shelf life on the condition that it is kept in a cool dry environment away from water and moisture.

If Patchfix Fine Filler has been wet or contains moisture it should not be used, the product should be discarded.

## FIRE

Patchfix Fine Filler, Patchfix Epoxy Binder and Techflow Epoxy Grout are non flammable,

ITEM NO	STOCK SIZE	COLOUR
<b>PATCHFIX FINE FILLER</b>		
272140	20kg	Beige
<b>PATCHFIX COARSE FILLER</b>		
272132	20kg	Beige
<b>PATCHFIX EPOXY BINDER</b>		
272159	1 Litre Kit	Clear / Amber
272167	4 Litre Kit	Clear / Amber
272175	20 Litre Kit	Clear / Amber
<b>TECHFLOW EPOXY GROUT</b>		
267783	4 litre kit	Grey
267791	16 litre kit	Grey

Product: Patchfix Fine Filler  
Issue Date: October 2001  
Issue No: 1  
Division: Construction  
Total Pages: 4

The representations and recommendations regarding the products are based on tests which we believe to be reliable. However, no guarantee of their accuracy can be made because of the great range of field conditions and variations encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with a limited warranty only, and on the condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik Findley Australia be liable to anyone except for replacement of the products or refund of the purchase price.

ALL SALES ARE EXPRESSLY LIMITED TO THE TERMS AND CONDITIONS OF SALE OF BOSTIK FINDLEY AUSTRALIA.

#### INTERNATIONAL OFFICES

**Bostik Findley Australia Pty Ltd**  
Tel: 03 9279 9333  
Fax: 03 9279 9270

**Bostik Findley New Zealand Pty Ltd**  
Tel: 0011 644 567 5119  
Fax: 0011 644 567 5412

**Bostik Findley Singapore Pty Ltd**  
Tel: 0011 6 5863 4088  
Fax: 0011 6 5863 4077

**Bostik Findley Malaysia Pty Ltd**  
Tel: 0011 644 567 5119  
Fax: 0011 644 567 5412

#### AUSTRALIAN BRANCHES

**Sydney**  
Tel: 02 8825 3488  
Fax: 02 8825 3411

**Brisbane:**  
Tel: 07 3265 2377  
Fax: 07 3265 5421

**Adelaide**  
Tel: 08 8244 0511  
Fax: 08 8244 0522

**Perth**  
Tel: 08 9331 7666  
Fax: 08 9331 7677

A.B.N. 79 003 893 838

